







QUICK-DRYING SCREED

SUITABLE TO TAKE ALL TYPES OF ADHESIVE FLOORING

Massettomix Pronto is a bagged pre-mixed screed mortar of semi-dry "damp soil" consistency that is ready for use after mixing with only water.

CHARACTERISTICS

Quick-drying

Massettomix Pronto gives rapid drying times for moisture-sensitive floors, which can be laid after only 4 days (on a thickness of 3 cm) and ceramics and stone to be fixed with adhesive, including "wet-on-wet", which can be laid after 24 h.

Reduced thickness

Can be used in thicknesses of 2 cm or above if bonded to a supporting layer, and does not require mesh reinforcement.

Strong, stable, durable, and CE-marked

It has high compressive strength (30 MPa), is CE-marked to denote conformity to EN 13813 (screed materials and floor screeds) and is dimensionally stable, non-deformable, and durable.

Also suitable for sloping surfaces and details: thanks to its semi-dry "damp soil" consistency it can also be applied to sloping or uneven surfaces internally or externally and can be moulded to create details, such as the falls of a screed for a shower.

TECHNICAL CHARACTERISTICS

Apparent packed density (approx.)	1.700 kg/m ³	
In-place density (approx.)	$> 2.000 \text{ kg/m}^3$	
Average compressive strength (EN 13813)	30 N/mm² (300 kg/cm²)	
Thermal conductivity λ	1,43 W/mK	
Laying of ceramic or stone finishes	after 24 h.	
Laying of moisture sensitive finishes (2% RH)	after 4 days (th. 3 cm)	
	after 9 days (th. 5 cm)	
Suggested thicknesses	Unbonded screed	≥ 3 cm
	Bonded screed	≥ 2 cm
	Floating screed	≥ 4 cm
Maximum area to be laid without joints	25 m ²	
Quantity required per 1 m ² of floor area	18-20 kg per 10 mm depth	
CE marking	EN 13813 CT-C30-F5	
Package: bags each of 25 kg on non-returnable wooden pallets, 64 bags/pallet - 1.600 kg/pallet.		
Storage life: 12 months from date of packaging.		







